

IBERPAN 400

TECHNICAL DATA-AVERAGE VALUES

Rev: 11/01/2018

PROPERTIES	TEST METHOD	UNITS	THICKNESSES mm			
			>30/40	>40/45	>45/60	>60/70
DENSITY (*)	EN 323	kg/m ³	450	450	450	450
INTERNAL BOND	EN 319	N/mm ²	0,20	0,20	0,20	0,20
BENDING STRENGTH	EN 310	N/mm ²	10	10	10	10
MODULUS OF ELASTICITY	EN 310	N/mm ²	1200	1200	1200	1200
THICKNESS SWELLING 24 H	EN 317	%	10	10	10	10
DIMENSIONAL MOVEMENT LENGTH/WIDTH	EN 318	%	0,25	0,25	0,25	0,25
DIMENSIONAL MOVEMENT THICKNESS	EN 318	%	5	5	5	5
SURFACE ABSORPTION (TWO FACES)	EN 382-1	mm	>150	>150	>150	>150
MOISTURE CONTENT	EN 322	%	7+/-3	7+/-3	7+/-3	7+/-3
GRIT CONTENT	ISO 3340	% Weight	≤ 0,05	≤ 0,05	≤ 0,05	≤ 0,05
FORMALDEHYDE CONTENT	EN ISO 12460-5	mg/100 g	≤ 8	≤ 8	≤ 8	≤ 8
SCREW HOLDING. EDGE	EN-320	N	350	350	425	425
SCREW HOLDING. SURFACE	EN-320	N	550	550	650	650
REACTION TO FIRE TABLA EN 13986:2004+A1:2015 I	EN 13501-1	Class	E (**)/ Efl E (**)	Efl E (**)/ Efl E (**)	Efl E (**)/ Efl E (**)	Efl E (**)/ Efl E (**)
SOUND ABSORPTION COEFFICIENT (A) (250 A 500 HZ)	EN 13984:2004+A1:2015	α	0,10	0,10	0,10	0,10
SOUND ABSORPTION COEFFICIENT (A) (1000 A 2000 HZ)	EN 13984:2004+A1:2015	α	0,20	0,20	0,20	0,20
THERMAL CONDUCTIVITY	EN 13984:2004+A1:2015	W/ (m·K)	0,07	0,07	0,07	0,07
AIRBORNE SOUND INSULATION (SURFACE MASS) (R)	EN 13986:2004+A1:2015	db	20	20	20	20
WATER VAPOUR PERMEABILITY DRY CUP	EN 13986:2004+A1:2015	μ	10	10	10	10
WATER VAPOUR PERMEABILITY WET CUP	EN 13986:2004+A1:2015	μ	4	4	4	4
BIOLOGICAL DURABILITY USE	EN 13986:2004+A1:2015	Class of use	1	1	1	1
CONTENT OF PENTACHLOROPHENOL (PCP)	EN 13986:2004+A1:2015	%	<5	<5	<5	<5

TOLERANCE ON NOMINAL DIMENSIONS

PROPERTIES	TEST METHOD	UNITS	THICKNESSES mm			
			>30/40	>40/45	>45/60	>60/70
THICKNESS	EN 324-1	mm	+/-0,3	+/-0,3	+/-0,3	+/-0,3
LENGTH/WIDTH	EN-324-1	mm	+/- 2	+/- 2	+/- 2	+/- 2
			mm/m	mm/m	mm/m	mm/m
			max +/- 5 mm.	max +/- 5 mm.	max +/- 5 mm.	max +/- 5 mm.
SQUARENESS	EN 324-2	mm/m	+/-2	+/-2	+/-2	+/-2
EDGE STRAIGHTNESS	EN-324-2	mm/m	+/-1,5	+/-1,5	+/-1,5	+/-1,5

(*) Values to be considered as a rough guide only.

(**) Commission Decision 2007/348/EC.

These physical-mechanical values improve/comply with those established in EN 622-5:2009 European Standard, Table 9. Requirements for MDF ultralight boards used in dry environments (UL1-MDF)..

IBERPAN 400 meets Class E1 requirements (analysed according EN ISO 12460-5) as defined in EN 622-1:2003 European Standard.

(SELECT)

Non dangerous product. Adequate ergonomic techniques and IPEs must be used when handling. Dust generated in cutting, sanding, drawmilling and other processes must be extracted from the working environment with the usual procedures in the wood industry as industrial vacuum systems and IPEs use must be observed according to law.